

Product Name: Baltic Blue
Hardness Value: 7



Shape: Angular
Size: 1-3mm

Product Description

An angular chipping which is a blue/grey colour.

Rock Type

Greywacke



Grading Analysis

Sieve Size	% Retained	% Passing	Range
5.00mm		100	100
3.35mm		92	>90
2.36mm		52	50-70
1.18mm		0.2	<15
0.60mm		0	<2

Physical Analysis

Properties	Value
Aggregate Abrasion Value - AAV	3.2
Aggregate Crushing Value - ACV	
Aggregate Impact Value - AIV	
Hardness (Mohs)	
Magnesium Sulphate Soundness (%)	
Polished Stone value (est) - PSV	66
Skid Resistant Value - SRV	
Specific Gravity	
Relative Density (Sat. Surface Dried) - SSD	
Relative Density (Apparent) - AP	
Oil Absorbtion (% by weight)	
10% Fines Value (Kn)	
Risk of iron staining (Estimate only) - RIS	<1
Los Angeles Coefficient:	14
Performance Scale:	5

Chemical Analysis (Typical)

Element	%
Aluminium (Al ₂ O ₃)	
Calcium (CaO)	
Calcium Carbonate (CaCO ₃)	
Iron (Fe ₂ O ₃)	
Magnesium (MgO)	
Magnesium Carbonate (MgCO ₃)	
Manganese (MnO)	
Phosphorus (P ₂ O ₅)	
Potassium (K ₂ O)	
Silica (SiO ₂)	
Sodium (Na ₂ O)	
Sulphate (So ₃)	
Titanium (TiO ₂)	
Loss on Ignition	