

**Product Name: White Grip**  
**Hardness Value: 8**



**Shape: Angular**  
**Size: 1-2mm**

## Product Description

Creamy white angular calcined chipping.



## Rock Type

Molochite

## Grading Analysis

Sieve Size	% Retained	% Passing	Range
2.80		100	100
2.00		100	95-100
1.70		90	77-98
1.00		7	0-15
0.71		0	<2

## Physical Analysis

Property	Value
Aggregate Abrasion Value - AAV	0.4
Aggregate Crushing Value - ACV	
Aggregate Impact Value - AIV	
Hardness (Mohs)	8
Magnesium Sulphate Soundness (%)	
Polished Stone value (est) - PSV	78
Skid Resistant Value - SRV	90-94
Specific Gravity	2.70
Relative Density (Sat. Surface Dried - SSD)	2.46
Relative Density (Apparent) - AP	
Oil Absorbtion (% by weight)	
10% Fines Value (Kn)	
Risk of iron staining (Estimate only) - RIS	*
Performance Scale:	5

## Chemical Analysis (Typical)

Element	%
Aluminium (Al <sub>2</sub> O <sub>3</sub> )	42
Calcium (CaO)	0.07
Calcium Carbonate (CaCO <sub>3</sub> )	
Iron (Fe <sub>2</sub> O <sub>3</sub> )	1.3
Magnesium (MgO)	0.30
Magnesium Carbonate (MgCO <sub>3</sub> )	
Manganese (MnO)	
Phosphorus (P <sub>2</sub> O <sub>5</sub> )	
Potassium (K <sub>2</sub> O)	2
Silica (SiO <sub>2</sub> )	54
Sodium (Na <sub>2</sub> O)	
Sulphate (So <sub>3</sub> )	
Titanium (TiO <sub>2</sub> )	0.07
Loss on Ignition	